

ATALAC MARINE

Type

Modified Alkyd resin enamel,
Modified synthetic alkyd resin based incorporating premium grade weather resistant pigments.
Finish coat on all appropriately primed interior and exterior building surfaces including wood,
steel, structural steel works, machinery, tank, pipelines, etc.

Characteristic

- Quick drying
- Good gloss and color retention
- Outstanding resistance to the effects weathering

Discription

Package	:	1 component
Color	:	Full Range Color
Finish	:	Super Gloss
Specific Gravity	:	1.0 – 1.2 (depend on colors)
Viscosity	:	60 Krebs units
Drying Time	:	Surface dry : 3 hours at 28 ⁰ C
DFT	:	Hard dry : 24 hours at 28 ⁰ C

Recommended Dry Film Thickness	:	25 – 35 microns per coat
Theorecal coverage	:	60 gr/m2 at 30 microns dft
Application losses	:	Approx. 40 %

When estimating working coverages, allow for application losses, surface irregularities, etc

Surface Preparation

Remove completely all dirt, grease, oil, water or other contaminants from surface to be coated.

Application Technical

Application Method	:	Roller, Airless spray and conventional spray
Thinner	:	Thinner 01

ReCoat Interval	:	Minimum : 12 hours at 28 ⁰ C
-----------------	---	---

1. Stir thoroughly until it is of uniform constituency prior to application.
2. Clean all equipment immediately after use with thinner or solvent

Precautions

This product is flammable, keep away from heat or open heat or open flames. As general rules, inhalation of solvent of paints mist and contact of liquid paint with skin or eyes should be avoided. Forced ventilation should be provided when applying in confinend spaces. Respiratory, skin and eyes protection are always recommended.

Product data

